

試驗報告



報告編號: TB-21-06155

C-21-15566

頁數: 1 OF 1

報告日期: 110年10月29日

工程名稱: 自測

承包商: -----

委託單位: 昇揚地板企業有限公司

供料廠商: -----

樣品名稱: Krono original HDF 高密度纖維板 10 mm

送驗人員: 昇揚地板企業有限公司-謝宗淵

收件日期: 110年10月21日

試驗日期: 110年10月21日~110年10月29日

備註: 1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責

未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

4.本樣品由SGS材料暨工程實驗室-台北(申請書號碼: HB-21-08746 C-21-37301,

收件日期: 110年10月20日)轉送至本實驗室執行本報告所示之試驗項目。

試驗結果:

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	0.3	0.05	CNS 11342(2014)
甲醛釋出量-平均值 (mg/L)	0.3	0.05	

註: 1.試驗結果低於方法偵測極限值(MDL)之測定值以"N.D."表示;

若高於方法偵測極限值(MDL),但低於定量極限值(QDL)時,以"<0.2"表示,

並括號註明其實測值

2.N.D. = Not Detected / 未檢出

3.本試驗之樣品不在TAF認證範圍內,故無法出具TAF標誌之報告

4.本試驗報告之試驗地點同實驗室地址

----- oOo -----

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.