

材料暨工程實驗室-台中

試驗報告

報告編號：TB-23-06293
C-23-15176頁數：1 OF 1
報告發行日期：112年11月21日

工程名稱：自測
 承包商：-----
 委託單位：昇揚地板企業有限公司
 供料廠商：-----
 樣品名稱：Krono span 強化卡扣超耐磨木地板
 送驗人員：昇揚地板企業有限公司-李沛臻
 收件日期：112年11月02日
 試驗日期：112年11月02日~112年11月21日
 備註：1.以上資料(會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供
 2.除非另有說明，此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意，此報告不可部分複製
 3.本樣品由SGS材料暨工程實驗室-台北(申請書號碼：HB-23-08417 C-23-35490
 收件日期：112年10月31日)轉送至本實驗室執行本報告所示之試驗項目。

試驗結果：

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	0.8	0.05	CNS 11342:2014
甲醛釋出量-平均值 (mg/L)	0.8	0.05	

- 註：1.試驗結果若低於方法偵測極限值(MDL)之測定值以"N.D."表示；
 若高於方法偵測極限值(MDL)，但低於定量極限值(QDL)時，以"<0.2"表示，
 並括號註明其實測值，定量極限值(QDL)為 0.2 mg/L
 2.N.D. = Not Detected / 未檢出
 3.樣品描述：木地板
 4.本實驗室執行試驗之地點同實驗室地址

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準


 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.